

Мембрана Rust-Oleum хидроизолационна за покриви и тераси 5 л, светлосива, Fillcoat

FILLCOAT® WATERPROOFING

DESCRIPTION

Instantly waterproof elastic paint for roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc.

RECOMMENDED USE

Waterproof finish of roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes etc. Recoatable with Dacfill, Coating PRT or Dacfill HZ.

TECHNICAL DATA

Density (g/cm ³):	1,05
Gloss Level:	Satin
Solids Content in weight:	52%
Solids content in volume:	43%

DRY TIMES BY 20° C/RV 50%

Touch dry:	4 h
Dry to recoat:	3 - 14 days with the same product. 6 weeks with a paint

RECOMMENDED WET FILM THICKNESS

1000 µm

RECOMMENDED DRY FILM THICKNESS

430 µm

THEORETICAL CONSUMPTION

1 coat of 1 - 1,5 l/m².

Apply 2 coats in combination with the Dacfill-fleece (see below).

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dust, mud, grease, moss and withered leaves carefully. The spots to be repaired are cleaned with a hard broom and sponged. After cleaning, Fillcoat can be applied directly on bituminous substrates, hard PVC, polyester, zinc, aluminium, glass, tiles, etc. Porous materials (concrete, stone, wood) must first be dried and pre-treated with a coat of Primer 44HS. In case of repeatedly repaired spots, important or active cracks, Fillcoat without fibres is to be reinforced with Dacfill-fleece: apply a coat of Fillcoat (about 1 l/m²), unroll Dacfill-fleece in it and cover it immediately with another coat of Fillcoat.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Can be applied during all weather conditions, except for snow.

APPLICATION & THINNING: BRUSH

Do not dilute.

APPLICATION & THINNING: ROLLER

Do not dilute.

APPLICATION & THINNING: AIRLESS SPRAY

Do not dilute. Nozzle: 18 - 23 / Pressure: 220 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended

CLEANING OF EQUIPMENT / SPILLS

Thinner 22 or white spirit.

REMARKS

Never apply to polystyrene insulation or onto new concrete (concrete should be at least 2 years old). Do not apply Fillcoat as priming coat under Dac Hydro Alu.

SAFETY DATA

VOC level:	485 g/l
VOC ready mix:	485 g/l
VOC category:	A/i
VOC limit:	500 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.



Продукт: [Мембрана Rust-Oleum хидроизолационна за покриви и тераси 5 л, светлосива, Fillcoat](#)

Категория: [Материали хидроизолационни](#)

Марка: [Марка Rust-Oleum](#)

Тип: [Мембрана Rust-Oleum](#)