

## Мембрана Rust-Oleum хидроизолационна за покриви и тераси с фибри, комплект 1 л, тъмносива, Fillcoat Fibres

### FILLCOAT® FIBRES WATERPROOFING

#### DESCRIPTION

Instantly waterproof elastic paint with crack-bridging fibres for roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc.

#### RECOMMENDED USE

Waterproof finish of roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc. Product is recoatable with Dacfill, Coating PRT or Dacfill HZ.

#### TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,03
Gloss Level:	Satin
Solids Content in weight:	52%
Solids content in volume:	43%

#### RECOMMENDED WET FILM THICKNESS

1000 µm

#### RECOMMENDED DRY FILM THICKNESS

430 µm

#### THEORETICAL CONSUMPTION

1 coat of 1,5 l/m<sup>2</sup>

#### PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### SURFACE PREPARATION

Remove dust, mud, grease, moss and withered leaves carefully. The spots to be repaired are cleaned with a hard broom and sponged. After cleaning, Fillcoat Fibres can be applied directly on bituminous substrates, hard PVC, polyester, zinc, aluminium, glass, tiles, etc. Porous materials (concrete, stone, wood) must first be dried and pre-treated with a coat of Primer 44HS. In case of repeatedly repaired spots, important or active cracks, apply Fillcoat Fibres crosswise over the cracks or fissures. Consumption: 1,5 kg/m<sup>2</sup> with a hawk or a block brush.

#### DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

#### APPLICATION CONDITIONS

Can be applied during all weather conditions, except for snow.

#### APPLICATION & THINNING: BRUSH

Do not dilute.

#### CLEANING OF EQUIPMENT / SPILLS

Thinner 22 or white spirit.

#### REMARKS

Never apply Fillcoat Fibres to polystyrene insulation or onto new concrete (concrete should be at least 2 year old). Do not apply Fillcoat Fibres as priming coat under Dac Hydro Alu.

#### SAFETY DATA

VOC level:	485 g/l
VOC readymix:	485 g/l
VOC category:	A/i
VOC limit:	500 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

#### SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.



Продукт: [Мембрана Rust-Oleum хидроизолационна за покриви и тераси с фибри, комплект 1 л, тъмносива, Fillcoat Fibres](#)

Категория: [Материали хидроизолационни](#)

Марка: [Марка Rust-Oleum](#)

Тип: [Мембрана Rust-Oleum](#)