

Грунд Body автобояджийски 1 кг, кафяв, RAL 969, Body 969 1K Anticorrosive Primer



Product Application: A 1K Anticorrosive primer

2 passes \implies Apply in thin layers over sanded areas only

Flash Point: 30 °C/ 86°F

Specific Gravity: 1.50 g/ cm³

Solid Content (No thinner): 72% Weight

VOC (2001/42/EC) 2004/42/IIБ(с)(540)410


The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 410 g/L

Theoretical Coverage: 7 m²/l at 600micron dry film thickness

Cleaning of equipment: Clean after final use with Body 740 ACRYL NORMAL



Compliant Spray gun 1.5-1.8 mm
3-4 bar inlet pressure
2x coat = 60 micron



Follow the application instructions mentioned in this TDS



HVLP 1.5-1.8 mm
0.7 bar atomization pressure
2x coat =60 micron

Бързосъхнещ антикорозионен грунд, който може да се нанася върху метални и дървени повърхности. Голямата устойчивост на влага, соленост, механични, химически и други екологични условия на север. Нанася с четка, валик или пистолет (дюза с диаметър 1.8 мм) и може да се разрежда 10-30% с разредител. Покритие: 7 м2/л

Продукт: [Грунд Body автобояджийски 1 кг, кафяв, RAL 969, Body 969 1K Anticorrosive Primer](#)

Категория: [Бои, кит и грунд автомобилни](#)

Бранд: [Body](#)

Категория бранд: [Грунд Body](#)

Ташев-Галвинг ООД
www.tashev-galving.com