

Technical Datasheet

Create Date:17.08.2020 - Seite1/1

Repair Stick Aluminium



non-rusting aluminium-filled

For the quick and nonrusting repair and bonding of metal parts. For the repair of cracks, holes and leaks in car bodies, gearboxes and tanks, window frames and profiles, and boats and models.

The WEICON Repair Stick Aluminium can be used in machine and system construction, in the automotive industry, in gear construction, window construction, model building and many other applications.

Technical Data

Base	Epoxy resin aluminium-filled
Texture	pasty
Colour after curing	aluminium
Mixing ratio by volume resin/hardener	1:1
Density of the mixture	1,9 g/cm³
Gap bridging max.	15 mm
Processing temperature	+10 to +35 °C
Curing temperature	+6 to +40 °C
Polt life for 25gr preparation and +20°C (+68°F)	4 min.
Handling strength (35% strength) after	10 min.
Capable of bearing mechanical loads (50% strength) after	60 min.
Final strength (100%) after	24 h
Pressure (DIN 53281-83)	80 N/mm²
Medium shear strength after 7 days at +20°C (+65°F) DIN EN 1465 at	Aluminium sandblasted: 4,2 N/mm²
Shore hardness D	75
Thermal conductivity (ASTM D 257)	0,65 W/m·K
Linear shrinkage	<1 %
Electrical resistivity (ASTM D 149)	5•10¹¹ Ohm/cm
Dielectric strength (ASTM D 149)	3,0 kV/mm

Thermal expansion coefficient (ISO 11359)	30-40 x 10 ⁻⁶ K ⁻¹
Temperature resistance	-50 to +120 briefly +150 °C
ISSA-Code	75.530.10/11
IMPA-Code	812965/66

Surface pre-treatment

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using WEICON Surface Cleaner).

Processing

WEICON Repair Sticks cover gaps of max. 15 mm per procedure. The pot life given is for a material quantity of 25 g at room temperature. If larger quantities are used, the curing time will be faster due to the typical reaction heat of epoxy resins (exothermic reaction). Similarly, higher ambient temperatures shorten the cure time (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Repair Sticks will keep for at least 18 months. Avoid direct sunlight.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10534057	Repair Stick Aluminium 57 g
10534115	Repair Stick Aluminium 115 g