


BODYSOFT

- VOC compliant with the regulations
- Two component polyester based putty
- Suitable for the filling of cavities and rotten areas of metallic and wooden surfaces
- Dries quickly
- It's easy to sand

General Technical Description



Mix 2-3% v/v Body Hardener with Bodysoft



Non force dry – 20-30 min / 23°C



IR drying 5-8 min

Surface :

- Suitable for the filling of cavities and rotten areas of metallic surfaces
- For wooden surfaces as well

Pretreatment / Cleaning of substrate:



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST


- Make sure the surface is air dried rather than wiped dry



- Make sure you always use appropriate face protection

Product Application:

⇒ Apply on metallic and wooden surfaces.

	100:3 mix with BODY HARDENER Pot life: 4min / 23°C		P80 – P120 Gives a fine, non porous surface
	Apply with the spatula		Store in a cool place
	Non force dry – 20-30min /23 °C		
	Short wave 5 – 8 min		Follow the application instructions mentioned in this TDS

Flash Point:	31 °C/ 88 °F
Specific Gravity:	1.90g/cm ³
Solid Content (No thinner):	87% Weight
VOC (2001/42/EC)	2004/42/II(b)(250)130
This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 250g/L. The VOC content in the ready for use form of this product is 130 g/L	
Theoretical Coverage:	-
Cleaning of equipment:	Clean after final use with Body 740 ACRYL NORMAL
Remarks:	• Application only with Body Hardener. Mix well with the putty. Do not add more than 3% as this may cause staining of the topcoat finish. • Do not apply to Etch Primer, 1K Filler, TPA substrates and soft old paintwork. • Do not apply at temperatures below +5 °C • It can be used by countries that do not adopt the VOC legislation as well. • Polyester materials have a limited shelf life. Store in a cool place and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers

I

Hardener paste contains organic peroxide and is an oxidant. If hardener comes in contact with the skin, wipe off immediately and wash with soap and water. After eye contact irrigate copiously with water and seek

HB BODY SA AUTOMOTIVE REFINISHING INDUSTRY, GREECE

<http://www.hbbody.com>

Page 2 of - 3

Ташев Галвинг ООД
www.tashev-galving.com

medical advice immediately.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 1/2008, June 2008.

