

VULCANO[®] S1

04

IT **Tubo trasparente in TPU a base estere rinforzato con spirale in acciaio ramato.** Spessore di parete costante 0,4 mm su tutti i diametri. Ottima robustezza, flessibilità e comprimibilità (circa 5:1), per un facile trasporto e stoccaggio. Buona resistenza ad abrasione, flessione, olii minerali, invecchiamento, agenti atmosferici, raggi UV ed ozono. Può essere reso conduttivo ($R < 10^2 \text{ Ohm/m}$) mettendo a terra la spirale.

• Falegnameria e industria del legno, depolverizzazione, piccoli aspiratori industriali; per impianti di aspirazione leggera di polveri abrasive e segatura e impiegato come guaina di protezione.

EN **Transparent, ester-based TPU hose reinforced with a copper-plated steel spiral.** Constant wall thickness 0,4 mm on all diameters. Excellent strength, flexibility and compressibility (approx. 5:1) for easy transport and storage. Good resistance to abrasion, bending, mineral oils, ageing, weathering, UV radiation and ozone. Can be made conductive ($R < 10^2 \text{ Ohm/m}$) by earthing the spiral.

• Carpentry and wood industry, dedusting, small industrial vacuum cleaners; for light extraction of abrasive dust and sawdust and used as a protective sleeve.

COD. W4
Ø mm 25-500



TPU a base estere
Ester based TPU hose

Spirale in acciaio ramato
Copper plated steel spiral




TABELLA TECNICA - TECHNICAL DATA		CODICE CODE	Ø INT. Ø INT.	SPES. MIN. MIN WALL TH.	PESO WEIGHT	DEPR. VAC.	R. CURVATURA BENDING	LG. ROTOLO COIL LGTH.	VOL. VOL.	FASCETTA DOPPIPONTE W2 DOUBLE BRIDGE W2
			mm/inch	mm	g/m m H ₂ O		mm	m	m ³	
costante 0,4 constant		W4010250000000*	25	0,4	130	0,4	25	20	0,05	-
		W4010300000000*	30	0,4	155	0,4	25	20	0,07	-
		W4010320000000*	32	0,4	160	0,4	25	20	0,07	-
		W4010350000000*	35	0,4	175	0,4	30	20	0,08	-
	F2 W2 p.122 Fascetta doppioponte W2 / Double bridge W2	W4010380000000*	38	0,4	190	0,4	30	20	0,08	-
		W4010400000000*	40	0,4	195	0,4	32	20	0,09	-
		W4010450000000*	45	0,4	220	0,4	36	20	0,10	-
		W4010510000000	51	0,4	205	0,4	40	20	0,11	-
	VULCANO 04 ET (cod. VE) p.86	W4010600000000	60	0,4	240	0,4	50	20	0,17	-
		W4010630000000	63	0,4	250	0,4	55	20	0,18	-
		W4010650000000*	65	0,4	255	0,4	56	20	0,19	-
		W4010700000000	70	0,4	360	0,4	60	20	0,20	-
ARTICOLI DELLA STESSA SERIE ITEMS IN THE SAME SERIES		W4010760000000	76	0,4	390	0,4	65	20	0,22	F2 W2 076.0 090.0
		W4010800000000	80	0,4	410	0,4	65	20	0,23	
		W4010820000000*	82	0,4	420	0,4	65	20	0,23	
		W4010900000000	90	0,4	460	0,4	75	20	0,28	
		W4011000000000*	100	0,4	505	0,3	85	15	0,31	F2 W2 100.0 127.0
		W4011020000000	102	0,4	515	0,3	85	15	0,32	
		W4011100000000	110	0,4	555	0,3	90	15	0,34	
		W4011150000000*	115	0,4	580	0,3	95	15	0,35	
		W4011200000000	120	0,4	600	0,25	100	15	0,37	F2 W2 130.0 190.0
		W4011270000000	127	0,4	635	0,25	105	15	0,39	
		W4011300000000	130	0,4	650	0,2	105	15	0,40	
		W4011400000000	140	0,4	700	0,2	115	15	0,64	
		W4011520000000	152	0,4	755	0,2	125	15	0,69	F2 W2 200.0 230.0
		W4011600000000	160	0,4	870	0,15	130	15	0,73	
		W4011650000000*	165	0,4	900	0,15	130	15	0,75	
		W4011700000000*	170	0,4	925	0,15	130	15	0,91	
		W4011800000000	180	0,4	975	0,15	150	15	0,96	F2 W2 250.0 330.0
		W4011820000000*	182	0,4	990	0,15	150	15	0,97	
		W4012030000000	203	0,4	1105	0,1	165	15	1,09	
		W4012200000000*	220	0,4	1195	0,1	185	10 m compr.	0,12	
		W4012280000000*	228	0,4	1235	0,1	185	10 m compr.	0,12	F2 W2 350.0 410.0
		W4012500000000*	250	0,4	1350	0,1	210	10 m compr.	0,15	
		W4012540000000	254	0,4	1375	0,1	210	10 m compr.	0,15	
		W4012790000000*	279	0,4	1505	0,08	230	10 m compr.	0,18	
		W4013050000000	305	0,4	1645	0,08	250	10 m compr.	0,22	
		W4013150000000*	315	0,4	1700	0,07	275	10 m compr.	0,23	
		W4013560000000*	356	0,4	1915	0,07	300	10 m compr.	0,29	
		W4014060000000*	406	0,4	2180	0,06	350	10 m compr.	0,38	
		W4014500000000*	450	0,4	2640	0,06	350	10 m compr.	0,47	-
		W4015000000000*	500	0,4	2930	0,06	350	10 m compr.	0,57	-

*Disponibile su richiesta, per quantitativi da concordare con l'ufficio vendite.

*Available on request, contact our sales office for more info and quantities.

I dati tecnici riportati sono stati misurati a 23°C e al 50% di umidità.

The technical data here reported have been measured at 23°C with 50% humidity.