


Тел Italfil сра заваръчна за ВИГ заваряване на нисколегирана стомана 2.0 мм, 1 м, SG2



Ташев-Галвинг ООД
www.tashev-galving.com



TIG WELDING RODS FOR CARBON AND LOW ALLOY STEELS

TIG WELDING RODS FOR CARBON AND LOW ALLOY STEELS

Type	diameter mm				Chemical Composition (average)								Application
	1.60	2.00	2.40	3.20	C%	Mn%	Si%	Cr%	Ni%	Mo%	Cu%		
ITB-SG1 AWS A6.18 : ER70S-3 EN ISO 1668 W 2Si	1.60	2.00	2.40	3.20	0.07	1.20	0.70	/	/	/	/	For carbon steels ---- type Fe 360 Fe 410 Fe 510 X 42 - X 52 - X 60 17 Mn 4 St 34 - St 42 - St 45 etc.	
ITB-SG2 AWS A6.18 : ER70S-6 EN ISO 1668 W 3Si1	1.60	2.00	2.40	3.20	0.07	1.40	0.80	/	/	/	/		
ITB-SG3 AWS A6.18 : ER70S-6 EN ISO 1668 W 4Si1	1.60	2.00	2.40	3.20	0.07	1.70	0.90	/	/	/	/		

Type	diameter mm				Chemical composition (average)								Application
	1.60	2.00	2.40	3.20	C%	Mn%	Si%	Cr%	Ni%	Mo%	Cu%		
ITB-SG2Mo AWS A6.28 : ER80S-G EN ISO 1668 W 2Mo EN ISO 21952-A-W MoSi	1.60	2.00	2.40	3.20	0.10	1.10	0.60	/	/	0.50	/	Tig welding rods for low alloy creep resistant Mo e al Cr Mo.	
ITB-SG3Mo AWS A6.28 ER80S-D2 EN 440 : G4MO	1.60	2.00	2.40	3.20	0.08	1.80	0.70	/	/	0.50	/		
ITB-SGCrMo1 AWS A6.28 ER80S - G EN ISO 21952-A-W CrMo 1Si	1.60	2.00	2.40	3.20	0.08	1.00	0.60	1.30	/	0.50	/		

Продукт: [Тел Italfil spa заваръчна за ВИГ заваряване на нисколегирана стомана 2.0 мм, 1 м, SG2](#)

Категория: [Електродръгово заваряване](#)

Бранд: [Italfil spa](#)

Категория бранд: [Тел Italfil spa](#)