

**Тел Metalweld заваръчна за ВИГ заваряване на INOX 2.4 мм, 1 м, MIGWELD 308LSi**



Ташев-Галвинг ООД  
[www.tashev-galving.com](http://www.tashev-galving.com)

# WELDING PRODUCTS

## CHEMICAL COMPOSITION (CAST ANALYSIS) (%)

		C	Mn	Si	S	P	Cr	Ni	Mo	Cb/Nb	Other elements
RW 307	min	-	4,50	0,30	-	-	17,0	7,0	-	-	-
	max	0,20	7,50	0,65	0,025	0,035	20,0	10,0	-	-	-
RW 307 Si	min	-	4,50	0,65	-	-	17,0	7,0	-	-	-
	max	0,20	7,50	1,00	0,025	0,035	20,0	10,0	-	-	-
RW 308L RW	min	-	1,00	-	-	-	18,0	9,0	-	-	-
	max	0,03	2,50	0,20	0,025	0,030	21,0	11,0	-	-	-
308L AWS RW	min	-	1,00	0,30	-	-	19,5	9,0	-	-	-
	max	0,03	2,50	0,65	0,030	0,030	22,0	11,0	-	-	-
308L Si RW	min	-	1,00	0,65	-	-	19,5	9,0	-	-	-
	max	0,03	2,50	1,00	0,030	0,030	22,0	11,0	-	-	-
308 H	min	0,04	1,00	0,30	-	-	19,5	9,0	-	-	-
	max	0,08	2,50	0,65	0,030	0,030	22,0	11,0	0,50	-	-
RW 309L RW	min	-	1,00	0,30	-	-	23,0	12,0	-	-	-
	max	0,03	2,50	0,65	0,030	0,030	25,0	14,0	-	-	-
309 Si RW	min	-	1,00	0,65	-	-	23,0	12,0	-	-	-
	max	0,12	2,50	1,00	0,030	0,030	25,0	14,0	0,75	-	-
309L Si RW	min	-	1,00	0,65	-	-	23,0	12,0	-	-	-
	max	0,03	2,50	1,00	0,030	0,030	25,0	14,0	-	-	-
309 H RW	min	-	1,00	0,30	-	-	23,0	12,0	-	-	-
	max	0,12	2,50	0,65	0,030	0,030	25,0	14,0	-	-	-
309L Mo RW	min	-	1,00	0,30	-	-	21,0	11,0	2,00	-	-
	max	0,03	2,50	0,65	0,030	0,030	25,0	15,5	3,50	-	-
310	min	0,08	1,00	0,30	-	-	25,0	20,0	-	-	-
	max	0,15	2,50	0,65	0,030	0,030	28,0	22,5	0,75	-	-
RW 312	min	-	1,00	0,30	-	-	28,0	8,0	-	-	-
	max	0,15	2,50	0,65	0,030	0,030	32,0	10,5	0,75	-	-
RW 316L RW	min	-	1,00	-	-	-	17,0	11,0	2,00	-	-
	max	0,03	2,50	0,20	0,025	0,030	20,0	14,0	3,00	-	-
316L AWS RW	min	-	1,00	0,30	-	-	18,0	11,0	2,00	-	-
	max	0,03	2,50	0,65	0,030	0,030	20,0	14,0	3,00	-	-
316L Si	min	-	1,00	0,65	-	-	18,0	11,0	2,00	-	-
	max	0,03	2,50	1,00	0,030	0,030	20,0	14,0	3,00	-	-

Продукт: [Тел Metalweld заваръчна за ВИГ заваряване на INOX 2.4 мм, 1 м, MIGWELD 308LSi](#)

Категория: [Електродъгово заваряване](#)

Бранд: [Metalweld](#)

Категория бранд: [Тел Metalweld](#)