



ШАМОТНА ОГНЕУПОРНА ТУХЛА

Свойства Properties	Показател Index	ШИ-40*	ШИ-36*	ШИ-32*	ШИ-30*	ШИ-28*	СТ-3**	СШ-2***
		SHI-40*	SHI-36*	SHI-32*	SHI-30*	SHI-28*	ST-3**	SSH-2***
Огнеупорност Refractoriness	°C	> 1730	> 1730	> 1730	> 1710	> 1670	> 1690	> 1670
Деформация под налягане Refractoriness under Load	T _{0.1} , °C	> 1350	> 1350	> 1320	> 1300	> 1270	-	-
Открита порьозност Apparent Porosity	%	< 22	< 22	< 23	< 24	< 22	< 24	17-25
Якост на натиск Cold Compressive Strength	MPa	> 20	> 20	> 20	> 20	> 25	-	-
Съдържание на Al ₂ O ₃ Contents of Al ₂ O ₃	%	> 40	> 36	> 32	> 30	> 28	> 30	> 28
БДС BDS****		4748:1988	4748:1988	4748:1988	4748:1988	4748:1988	4674:1988	4674:1988

* - За изделия с общо предназначение / For shapes for general use

** - За стопорни тръби / For trumpet tubes

*** - За изделия за сифонно разливане на стомана / For casting assortment

**** - Bulgarian National Standard

Заводски № Shape No	Размери в mm / Dimensions in mm			Тегло, kg Weight, kg
	l	b	h	
1	250	123	65	4,1
2	230	113	65	3,5
140	300	150	65	6,0
567	171	113	65	2,6
568	230	171	65	5,1
2787	230	113	50	2,7
3140	220	110	60	3,0
3140A	220	110	50	2,5
3503	345	113	76	6,0

